

Approach for the Fuel Element Failure Section of NEEP-423

- **Very Comprehensive Treatment of pre-1977 period given in:**

"The Main Causes of Fuel Failure in Water-Cooled Power Reactors"

by

F. Garzaolli, R. von Jan, H. Stehle

Atomic Energy Review, Vol. 17, No. 1, p. 31 (1979)

- **Very Comprehensive review of the period in the 1980's and up to mid 1990's:**

"Proceedings of the 1997 International Topical Meeting on Light Water Reactor Fuel Performance"

Portland, Oregon, March 2-6, 1997

Current Areas of R & D Focus

General

1.) Fuel and Cladding Material Properties at High Burnup

(Concern here is for transient conditions)

- **Thermal diffusivity is different (lab vs in-reactor)**
- **Cladding ductility shows wide scatter due to H₂ concentration, sample preparation, and measurement techniques**
- **Must understand in-reactor behavior**

2.) Failure Root cause Investigation

(To achieve zero defects, must understand causes)

- **Poolside inspections valuable for identification**
- **Expensive hotcell studies done only if poolside investigation does not work**

3.) Updated Codes and Analytical Tools

(Especially important for high BU in PWR's)

- **Gadolinia absorbers, local boiling, effect of boiling on flow properties**
- **Integrated nuclear and thermal hydraulic codes**

Current Areas of R & D Focus (cont.)

4.) Transient Fuel Behavior

(Controversy over reactor-initiated accidents [RIA])

- **All parties (regulators, utilities, and vendors) agree that simulated conditions are much more severe than reality**
- **Particularly interested in post-LOCA and post-DNB conditions**
- **Difficult to conduct meaningful experiments**

5.) Next Generation Fuel

(Concern here is to increase reliability and operational flexibility)

- **New fuel designs and materials**
- **>60 GWd/T burnup, load following, extended cycle time**
- **Water chemistry changes**

Current Areas of R & D Focus (cont.)

PWR Specific

1.) Cladding Corrosion

(Plant surveillance shows that cladding corrosion is limiting further BU extension)

2.) Water Chemistry Control

- Codes are now available to predict corrosion rate as a function of:

heat flux
coolant temperature
neutron fluence
cladding hydrogen content
cladding intermetallic particles
heat treatment
coolant Li concentration

- Recommendation is to raise pH and reduce source of crud

(requires 30% enriched ^{10}B to keep Li concentration < 3 ppm)

Current Areas of R & D Focus (cont.)

BWR Specific

- 1.) Finding cladding barrier that is resistant to PCI failures**
- 2.) Reduce "fuel washout" from failed fuel**